阅读申明

- 1.本站收集的数据手册和产品资料都来自互联网,版权归原作者所有。如读者和版权方有任何异议请及时告之,我们将妥善解决。
- 2.本站提供的中文数据手册是英文数据手册的中文翻译,其目的是协助用户阅读,该译文无法自动跟随原稿更新,同时也可能存在翻译上的不当。建议读者以英文原稿为参考以便获得更精准的信息。
- 3.本站提供的产品资料,来自厂商的技术支持或者使用者的心得体会等,其内容可能存在描 叙上的差异,建议读者做出适当判断。
- 4.如需与我们联系,请发邮件到marketing@iczoom.com,主题请标有"数据手册"字样。

Read Statement

- 1. The datasheets and other product information on the site are all from network reference or other public materials, and the copyright belongs to the original author and original published source. If readers and copyright owners have any objections, please contact us and we will deal with it in a timely manner.
- 2. The Chinese datasheets provided on the website is a Chinese translation of the English datasheets. Its purpose is for reader's learning exchange only and do not involve commercial purposes. The translation cannot be automatically updated with the original manuscript, and there may also be improper translations. Readers are advised to use the English manuscript as a reference for more accurate information.
- 3. All product information provided on the website refer to solutions from manufacturers' technical support or users the contents may have differences in description, and readers are advised to take the original article as the standard.
- 4. If you have any questions, please contact us at marketing@iczoom.com and mark the subject with "Datasheets".





SPECIFICATION

• Supplier : Samsung electro-mechanics • Samsung P/N : CL10C120FB8NNNC

• Product : Multi-layer Ceramic Capacitor • Description : CAP, 12pF, 50V, ±1%, C0G, 0603

A. Samsung Part Number

<u>CL</u> <u>10</u> <u>C</u> <u>120</u> <u>F</u> <u>B</u> <u>8</u> <u>N</u> <u>N</u> <u>N</u> <u>N</u> <u>C</u> ① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨ ⑩ ⑪

| ① 5 | Series | Samsung Multi-layer Ceramic Capacitor | | | | | | | |
|------------|---------------|---------------------------------------|----------|-----|----------------|---------|----|---------------|--------------|
| 2 5 | Size | 0603 (inch c | code) L: | 1.6 | ± 0.1 | mm | W: | 0.8 ± 0.1 | mm |
| 3 [| Dielectric | C0G | | (8) | Inner el | actrada | N | li | |
| _ | | | | • | | | - | | |
| 4 (| Capacitance | 12 pF | | | Termina | ation | С | u | |
| 5 (| Capacitance | ±1 % | | | Plating | | S | n 100% | (Pb Free) |
| t | tolerance | | | 9 | Product | t | N | lormal | |
| 6 F | Rated Voltage | 50 V | | 10 | Special | | R | eserved for | future use |
| 7 1 | Thickness | 0.8 ± 0.1 | mm | 11) | Packagi | ing | С | ardboard Ty | ype, 7" reel |

B. Samsung Reliablility Test and Judgement condition

| | Performance | Test condition | | | | | |
|-------------------|--|--------------------------------------|--|--|--|--|--|
| Capacitance | Within specified tolerance | 1Mb±10% 0.5~5Vrms | | | | | |
| Q | 640 min | | | | | | |
| Insulation | 10,000Mohm or 500Mohm⋅ <i>μ</i> F | Rated Voltage 60~120 sec. | | | | | |
| Resistance | Whichever is Smaller | | | | | | |
| Appearance | No abnormal exterior appearance | Microscope (×10) | | | | | |
| Withstanding | No dielectric breakdown or | 300% of the rated voltage | | | | | |
| Voltage | mechanical breakdown | | | | | | |
| Temperature | COG | | | | | | |
| Characterisitcs | (From -55 $^{\circ}$ C to 125 $^{\circ}$ C, Capacitance change shoud be within ±30PPM/ $^{\circ}$ C) | | | | | | |
| Adhesive Strength | No peeling shall be occur on the | 500g·F, for 10±1 sec. | | | | | |
| of Termination | terminal electrode | | | | | | |
| Bending Strength | Capacitance change : | Bending to the limit (1mm) | | | | | |
| | within ±5% or ±0.5pF whichever is larger | with 1.0mm/sec. | | | | | |
| Solderability | More than 75% of terminal surface | SnAg3.0Cu0.5 solder | | | | | |
| | is to be soldered newly | 245±5℃, 3±0.3sec. | | | | | |
| | | (preheating : 80~120℃ for 10~30sec.) | | | | | |
| | | | | | | | |
| Resistance to | Capacitance change : | Solder pot : 270±5℃, 10±1sec. | | | | | |
| Soldering heat | within ±2.5% or ±0.25pF whichever is larger | | | | | | |
| | Tan δ, IR : initial spec. | | | | | | |

| | Performance | Test condition | | | | |
|------------------|---|--|--|--|--|--|
| Vibration Test | Capacitance change : | Amplitude : 1.5mm | | | | |
| | within ±2.5% or ±0.25pF whichever is larger | From 10Hz to 55Hz (return : 1min.) | | | | |
| | Tan δ, IR : initial spec. | 2hours × 3 direction (x, y, z) | | | | |
| Moisture | Capacitance change : | With rated voltage | | | | |
| Resistance | within ±7.5% or ±0.75pF whichever is larger | 40±2℃, 90~95%RH, 500+12/-0hrs | | | | |
| | Q: 140 min | | | | | |
| | IR : 500Mohm or 25Mohm $\cdot \mu$ F | | | | | |
| | Whichever is Smaller | | | | | |
| High Temperature | Capacitance change : | With 200% of the rated voltage | | | | |
| Resistance | within ±3% or ±0.3pF whichever is larger | Max. operating temperature | | | | |
| | Q: 305 min | 1000+48/-0hrs | | | | |
| | IR: 1000Mohm or 50Mohm $\cdot \mu$ F | | | | | |
| | Whichever is Smaller | | | | | |
| Temperature | Capacitance change : | 1 cycle condition | | | | |
| Cycling | within ±2.5% or ±0.25pF whichever is larger | Min. operating temperature → 25°C | | | | |
| | Tan δ, IR : initial spec. | $ ightarrow$ Max. operating temperature $ ightarrow$ 25 $^{\circ}\!$ | | | | |
| | | | | | | |
| | | | | | | |
| | | 5 cycle test | | | | |

C. Recommended Soldering method :

Reflow (Reflow Peak Temperature : 260+0/-5 $^{\circ}$ C, 10sec. Max)

^{*} For the more detail Specification, Please refer to the Samsung MLCC catalogue.